

**BAMBOO (BETUNG SPECIES) FIBER  
COMPOSITE PLATE FOR EXTERNAL  
STRENGTHENING OF RC BEAMS**

**JACKY MOH NEING SHENG**

**B. ENG (HONS.) CIVIL ENGINEERING**

**UNIVERSITI MALAYSIA PAHANG**



## **SUPERVISOR'S DECLARATION**

I hereby declare that I have checked this thesis and in my opinion, this thesis is adequate in terms of scope and quality for the award of the Bachelor Degree of Civil Engineering

---

(Supervisor's Signature)

Full Name : DR CHIN SIEW CHOO

Position : SENIOR LECTURER

Date : 8 JUNE 2018



## **STUDENT'S DECLARATION**

I hereby declare that the work in this thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at Universiti Malaysia Pahang or any other institutions.

---

(Student's Signature)

Full Name : JACKY MOH NEING SHENG

ID Number : AA14082

Date : 8 JUNE 2018

**BAMBOO (BETUNG SPECIES) FIBER COMPOSITE PLATE FOR EXTERNAL  
STRENGTHENING OF RC BEAMS**

**JACKY MOH NEING SHENG**

Thesis submitted in fulfillment of the requirements  
for the award of the  
Bachelor Degree in Civil Engineering

Faculty of Civil Engineering and Earth Resources  
**UNIVERSITI MALAYSIA PAHANG**

**JUNE 2018**

## **ACKNOWLEDGEMENTS**

I would like to take this opportunity to acknowledge all the parties who helped me in completing this research. First, I would to express my appreciation to my supervisor, Dr. Chin Siew Choo for her guidance, idea and support throughout this research. Through her useful recommendation, knowledge and informative discussion, I am being able to complete this study.

Next, I would like to express my gratitude towards my university, Universiti Malaysia Pahang for providing me a platform to conduct and complete this research. Also, with all the facilities, equipment and machineries, I am being able to carry out all the relevant tests. Not to forget the concrete lab staffs for their professional guidance and clear instructions during the laboratory works.

Apart from that, I would like to thank all the lecturers whom have taught me in every semester. They have indeed helped me to understand more on the knowledge and theories in this field of study.

Lastly, special thanks to all my friends who are always willing to help and share their knowledge, even help for heavy lab works. They have indeed helped me to save time and cost for completing this study. I am also grateful to my family for their encouragement and support all the way to the completion of my study.

## ABSTRAK

Gentian semula jadi telah digunakan untuk menggantikan gentian sintetik dalam pembuatan komposit kerana gentian semula jadi lebih mesra alam berbanding dengan gentian sintetik. Satu penyelidikan telah dijalankan untuk mengenal pasti sifat mekanikal buluh spesies Betung dan potensinya untuk difabrikasikan sebagai komposit berasaskan gentian buluh (BFCP) sehubungan dengan penggunaannya dalam menambahkan kekuatan luaran rasuk konkrit bertelulang. Dalam kajian ini, buluh yang digunakan diperoleh dari Raub, Pahang. Ciri-ciri mekanikal buluh mentah dan kering telah dikaji melalui ujian mampatan dan ujian tegangan. BFCPs dalam nisbah isipadu gentian 0.4 telah difabrikasikan dan diuji dengan ujian lenturan (ASTM D790-03) dan ujian tegangan (ASTM D3039) untuk menentukan sifat-sifat mekanikalnya. Ujian pemuatan empat titik telah dijalankan untuk mengkaji kekuatan rasuk konkrit bertelulang yang dipasang dengan BFCP. Hasil kajian menunjukkan bahawa buluh spesies Betung mempunyai kepadatan sebanyak  $0.807 \text{ g/cm}^3$ . Dalam ujian mampatan, sampel buluh yang diuji gagal dalam dua mod, iaitu penghancuran gentian dan retakan gentian. Sampel buluh yang kering telah mencapai kekuatan mampatan sebanyak 19.5 % berbanding dengan sampel buluh yang mentah. Sebaliknya, keputusan menunjukkan bahawa kekuatan tegangan sampel mentah telah bertambah sebanyak 45 % berbanding dengan sampel yang kering. Selain itu, dalam ciri-ciri mekanikal, BFCP telah menunjukkan ketinggian sebanyak 666 % dan 178 % dalam kedua-dua kekuatan lenturan dan kekuatan tegangan berbanding dengan sampel epoksi. Pengekatan antaran serat buluh dengan resin epoksi dalam BFCP telah menambahbaikkan ikatan struktur dan ciri-ciri mekanikalnya. Melalui ujian pemuatan empat titik, data menunjukkan bahawa rasuk konkrit bertelulang yang ditampalkan dengan BFCP sebanding dengan rasuk konkrit kawalan dengan nisbah kekuatan sebanyak 96 % dan 97 %. Kajian juga menunjukkan kekuatan rasuk konkrit yang diperkuatkan dengan BFCP telah meningkat sebanyak 10-12 % berbanding dengan rasuk konkrit yang tanpa sebarang pengukuhan. Dalam pemerhatian corak-corak retakan, hanya sedikit retakan yang muncul di bahagian yang ditampal dengan BFCP. Pemasangan BFCP mampu mengalihkan retakan tegak ke pinggir plat dengan membentuk retakan pepenjuru. Ini membuktikan bahawa aplikasi BFCP sangat berkesan untuk menambahbaikkan kekuatan lenturan dan ia berpotensi untuk digunakan sebagai bahan pengukuhan luaran untuk memulihkan kekuatan rasuk konkrit bertelulang.

## ABSTRACT

Natural fibers are being introduced to replace the synthetic fiber in the manufacturing of fiber composites due to its environmental friendly behavior. A research had been conducted to investigate the mechanical properties of bamboo (Betung species) and its potential to be used as bamboo fiber composite plate (BFCP) for the external strengthening of reinforced concrete (RC) beams. Raw bamboo culms were obtained from Raub, Pahang. Mechanical behaviour of raw and dried bamboo specimens was tested under compression test and tension test. All the BFCPs with 0.4 fiber-to-volume ratio have been fabricated and tested for flexural test (ASTM D790-03) and tensile test (ASTM D3039) to determine the mechanical properties. Four-point loading test was conducted to study the behaviour of reinforced concrete (RC) beam under external strengthening effect with BFCP. The result showed that bamboo of Betung species has a density of  $0.807 \text{ g/cm}^3$ . In compression test, bamboo culms fail in two modes: fiber cracking and fiber crushing. Dried bamboo specimens recorded 19.5 % higher in compression strength than raw bamboo specimens. There was an improvement of 45 % of average tensile strength in raw bamboo samples compared to dried specimens. In terms of mechanical behaviour, BFCP has higher flexural and tensile strength than pure epoxy samples where the flexural and tensile strength of BFCP increased by 666 % and 178 % respectively. The interfacial adhesion between the bamboo fiber and epoxy resin in BFCP greatly improved the structural bonding and mechanical properties. From the four-point loading test, BFCP strengthened beams had achieved the total load bearing capacity of 96 % and 97 % compared to solid control beam. Compared with un-strengthened beam, the load bearing capacity of BFCP strengthened beam increased by 10 % and 12 %. Installation of BFCP manage to divert the vertical cracks at the tension zone to the edge of the plate forming diagonal cracks. This proved that BFCP has potential to be used as external strengthening material in RC beams.

## **TABLE OF CONTENT**

**DECLARATION**

**TITLE PAGE**

**ACKNOWLEDGEMENTS** **ii**

**ABSTRAK** **iii**

**ABSTRACT** **iv**

**TABLE OF CONTENT** **v**

**LIST OF TABLES** **ix**

**LIST OF FIGURES** **x**

**LIST OF SYMBOLS** **ii**

**LIST OF ABBREVIATIONS** **iii**

**CHAPTER 1 INTRODUCTION** **1**

1.1 Research Background 1

1.2 Problem Statement 3

1.3 Research Objectives 3

1.4 Scope of Study 4

1.5 Research Significance 5

**CHAPTER 2 LITERATURE REVIEW** **6**

2.1 Introduction 6

2.2 Plant Fiber 6

2.3 Bamboo Fiber 8

2.3.1 Mechanical Properties 9



2.4	Extraction of Bamboo Fiber	12
2.4.1	Mechanical Extraction	13
2.4.2	Chemical Extraction	13
2.4.3	Combined Mechanical and Chemical Extraction	14
2.5	Surface Treatment Method	15
2.5.1	Pre-treatment	15
2.5.2	Chemical/Alkaline Treatment	15
2.6	Polymer Resin	16
2.6.1	Epoxy	17
2.7	Bamboo Fiber Reinforced Composite (BFRC)	18
2.7.1	Hand lay-up method	20
2.7.2	Fiber Volume Ratio	20
2.8	Mechanical Test on Fiber Composite	22
2.8.1	Flexural Test	22
2.8.2	Tensile Test	24
2.9	RC Beams Strengthened Externally by NFRC	25
2.9.1	Sisal Fiber Reinforced Composite	25
2.9.2	Kenaf Fiber Reinforced Composite	26
2.9.3	Bamboo Fiber Reinforced Composite Plate	27
2.10	Summary	28
<b>CHAPTER 3 METHODOLOGY</b>		<b>29</b>
3.1	Introduction	29
3.2	Research Methodology	30
3.3	Preparation of Materials	31
3.3.1	Bamboo specimen	31

3.3.2	Bamboo Fiber	32
3.3.3	Thermosetting Matrix	33
3.4	Testing of Bamboo Specimen	33
3.4.1	Density Test	33
3.4.2	Compression Test	34
3.4.3	Tensile Test	35
3.5	Fabrication of Bamboo Fiber Composite Plate (BFCP)	35
3.6	Testing of BFCP	37
3.6.1	Tensile Test	37
3.6.2	Flexural Test	38
3.7	Reinforced Concrete Beam Casting	39
3.7.1	Erection of Formwork	39
3.7.2	Reinforcement Bar	39
3.7.3	Concrete	41
3.7.4	Beam Casting and Curing	41
3.8	BFCP Strengthening System	42
3.8.1	Sikadur® 30 Adhesive	42
3.8.2	Strengthening Configuration	43
3.9	Laboratory Testing	44
3.9.1	Slump Test	44
3.9.2	Compression Test	44
3.9.3	Four Point Loading Test	45
3.10	Summary	46
<b>CHAPTER 4 RESULTS AND DISCUSSION</b>		<b>47</b>
4.1	Introduction	47

4.2	Density Test	47
4.3	Mechanical Test	48
4.3.1	Fresh and Hardened Properties of Concrete	48
4.3.2	Bamboo Specimen	50
4.3.3	Bamboo Fiber Composite Plate (BFCP)	55
4.3.4	RC Beam under Four-Point Loading Test	58
<b>CHAPTER 5 CONCLUSION</b>		<b>66</b>
5.1	Introduction	66
5.2	Conclusion	66
5.3	Recommendation	67
5.4	Limitation	67
<b>REFERENCES</b>		<b>68</b>
<b>APPENDIX A GANTT CHART</b>		<b>75</b>
<b>APPENDIX B CALCULATION FOR THE AMOUNT OF MATERIAL USED FOR BAMBOO FIBER COMPOSITE PLATE (BFCP) FABRICATION</b>		<b>76</b>
<b>APPENDIX C CONCRETE MIX DESIGN COMPUTATION AND SUMMARY</b>		<b>77</b>
<b>APPENDIX D DATA SHEET OF SIKADUR® 30 EPOXY LAMINATING RESIN</b>		<b>78</b>
<b>APPENDIX E DATA SHEET OF EPOXY D.E.R 311</b>		<b>79</b>
<b>APPENDIX F DATA SHEET OF HARDENER JOINTMINE 905-3S</b>		<b>80</b>

## LIST OF TABLES

<b>Table 2.1:</b> Fiber and origin of countries.	8
<b>Table 2.2:</b> Comparative properties of bamboo fiber based reinforced composites.	11
<b>Table 2.3:</b> Compression strength for different types of bamboo species.	12
<b>Table 2.4:</b> Mechanical properties of bamboo fibers based on the extraction procedures.	14
<b>Table 2.5:</b> Uniaxial tensile test results of bamboo fibers with alkaline treatment and without alkaline treatments.	16
<b>Table 2.6:</b> Comparative study of polyester, epoxy and inyl ester resins.	17
<b>Table 2.7:</b> Flexural properties for bio-epoxy and traditional epoxy.	18
<b>Table 2.8:</b> Comparison between bamboo fiber and glass fiber in several terms.	19
<b>Table 2.9:</b> Tensile properties of jute and bamboo composites.	19
<b>Table 2.10:</b> Flexural properties of jute and bamboo composites.	19
<b>Table 2.11:</b> Flexural properties of hemp fiber composites at different fiber contents.	22
<b>Table 2.12:</b> Ultimate flexural strength of plain polyester and various fiber composite.	23
<b>Table 3.1:</b> Summary of tests involved with bamboo specimen, bamboo fiber composite plate (BFCP) and beam specimens.	46
<b>Table 3.2:</b> Summary for beams specimens.	46
<b>Table 4.1:</b> The density for five specimens of bamboo culms.	47
<b>Table 4.2:</b> Compressive strength of concrete cube.	49
<b>Table 4.3:</b> Dimension for raw and dried bamboo specimen.	51
<b>Table 4.4:</b> Summary for load and compressive strength.	52
<b>Table 4.5:</b> Dimension of raw and dried bamboo splints for tensile test.	54
<b>Table 4.6:</b> Comparison of tensile strength between raw and dried bamboo specimens.	54
<b>Table 4.7:</b> Summary of flexural test for pure epoxy and BFCP specimens.	56
<b>Table 4.8:</b> Summary of tensile test.	57
<b>Table 4.9:</b> Summary of four-point loading test.	64
<b>Table 4.10:</b> Summary of crack pattern and failure mode.	65

## LIST OF FIGURES

<b>Figure 2.1:</b> Plant based fiber classification.	7
<b>Figure 2.2:</b> The relationship between tensile strength and fiber volume ratio.	21
<b>Figure 2.3:</b> Flexural strength of polyester and epoxy composite varying fiber content.	23
<b>Figure 2.4:</b> Tensile strength for various volume fraction of fiber.	24
<b>Figure 2.5:</b> Stress vs Strain Graph of different composite materials.	25
<b>Figure 2.6:</b> Summary for beam test strengthened by SFRC, CFRP and GFRP.	26
<b>Figure 2.7:</b> Experiment results for control beam, KFRP laminate strengthened beam and CFRP laminate strengthened beam.	27
<b>Figure 3.1:</b> Raw bamboos (Betung species) were harvested from Raub, Pahang.	31
<b>Figure 3.2:</b> The nodal part was removed to ease the extraction of fiber.	32
<b>Figure 3.3:</b> Mill rolling was used for extraction of bamboo fiber.	33
<b>Figure 3.4:</b> Water displacement method was used in density test.	34
<b>Figure 3.5:</b> Compression test was conducted on hollow bamboo specimen.	34
<b>Figure 3.6:</b> The bamboo splint was fixed to UTM equipment for tensile test.	35
<b>Figure 3.7:</b> Hand lay-up method was used for the fabrication of BFCP.	36
<b>Figure 3.8:</b> BFCP samples.	36
<b>Figure 3.9:</b> Pure epoxy samples.	37
<b>Figure 3.10:</b> BFCPs with larger dimension were prepared to be applied on RC beams.	37
<b>Figure 3.11:</b> Tensile test for BFCP.	38
<b>Figure 3.12:</b> Flexural test for neat epoxy specimen.	38
<b>Figure 3.13:</b> Silicone gun was used to seal up gaps inside the formwork.	39
<b>Figure 3.14:</b> Illustration of rebar in solid control beam (CB).	40
<b>Figure 3.15:</b> Illustration of rebar in BFCP strengthened beam (ST-B).	40
<b>Figure 3.16:</b> Spacer blocks were tied with the rebar.	40
<b>Figure 3.17:</b> Ready-mixed concrete was supplied by PAMIX Sdn. Bhd.	41
<b>Figure 3.18:</b> All the beams were casted simultaneously.	42
<b>Figure 3.19:</b> Concrete cubes were prepared.	42
<b>Figure 3.20:</b> Sikadur®-30 epoxy laminating resin consisted of two parts: Part A white resin and Part B black hardener.	43
<b>Figure 3.21:</b> The surface of beam was roughed before installation of BFCP.	43
<b>Figure 3.22:</b> BFCPs were attached to the RC beams.	44
<b>Figure 3.23:</b> Compression test for one of the cubes after curing for 7 days.	44

<b>Figure 3.24:</b> Schematic diagram for four-point loading test.	45
<b>Figure 3.25:</b> The setting of four-point bending test for control beam.	45
<b>Figure 4.1:</b> Shear slump was observed during slump test.	48
<b>Figure 4.2:</b> Graph of compressive strength of concrete against sample age.	49
<b>Figure 4.3:</b> Cracking of bamboo fibers.	51
<b>Figure 4.4:</b> Crushing of bamboo fibers.	51
<b>Figure 4.5:</b> Graph of stress versus strain for the raw and dried bamboo specimen.	52
<b>Figure 4.6:</b> Failure of bamboo splints at middle node under tensile load.	53
<b>Figure 4.7:</b> Graph of stress versus strain under tensile test.	55
<b>Figure 4.8:</b> Graph of stress versus strain under flexural test.	56
<b>Figure 4.9:</b> Graph of stress versus strain under tensile test.	58
<b>Figure 4.10:</b> Graph of load versus deflection for solid control beams (CB).	59
<b>Figure 4.11:</b> Graph of load versus deflection for un-strengthened beams (UST-B).	59
<b>Figure 4.12:</b> Graph of load versus deflection for BFCP strengthened beams.	60
<b>Figure 4.13:</b> Load deflection curve for different beam specimens.	61
<b>Figure 4.14:</b> Crack pattern in CB 1.	62
<b>Figure 4.15:</b> Crack pattern in CB 2.	62
<b>Figure 4.16:</b> Crack pattern in CB 3.	62
<b>Figure 4.17:</b> Crack pattern in UST-B1.	63
<b>Figure 4.18:</b> Crack pattern in UST-B2.	63
<b>Figure 4.19:</b> Crack pattern in ST-B1.	64
<b>Figure 4.20:</b> Crack pattern in ST-B2.	64

## LIST OF SYMBOLS

%	Percentage
mm	Millimeter
m	meter
N/mm <sup>2</sup>	Newton per millimeter square
g/cm <sup>3</sup>	Gram per centimeter cube
mL	Milliliter
N	Newton
kN	Kilo Newton
°C	Degree Celsius
g	Gram
mm/min	Millimeter per minute
mm <sup>2</sup>	Millimeter square
MPa	Mega Pascal
D	Distance from the support (mm)
V	Volume

## **LIST OF ABBREVIATIONS**

BFCP	Bamboo Fiber Composite Plate
BFCPs	Bamboo Fiber Composite Plates
CAN	Chemical Assisted Natural
CB	Control Beam
CFRC	Carbon Fiber Reinforced Composite
CO <sub>2</sub>	Carbon Dioxide
GFRC	Glass Fiber Reinforced Composite
INBAR	International Network for Bamboo and Rattan
LBC	Laminated Bamboo Composite
NFRCs	Natural Fiber Reinforced Composites
NaOH	Sodium Hydroxide
NFCP	Natural Fiber Composite Plate
RC	Reinforced Concrete
RM	Ringgit Malaysia
SFCP	Synthetic Fiber Composite Plate
SFCPs	Synthetic Fiber Composite Plates
ST-B	Strengthened Beam
US\$	United States Dollar
UST-B	Un-strengthened Beam
UTM	Universal Testing Machine



## CHAPTER 1

### INTRODUCTION

#### 1.1 Research Background

Due to the concerns over environment, there has been a lot of research in recent years towards the potential of natural fiber as an alternative to synthetic fiber especially in construction industries. Synthetic fibers that commonly used are polyethylene, aramid, polyesters, carbon and others hybrid fibers. Synthetic fibers are used due to their high performance in terms of strength, susceptible to fungus attack and water resistance. However, the mode of disposal of these artificial fibers becomes an issue which may threaten the environment because they are non-biodegradable. Hence, there are extensive of studies on the application of natural plant fibers like jute, kenaf, sisal, silk and bamboo fiber as an alternative to the synthetic fibers (Tong, 2017). Compare with artificial fibers, nature fibers tend to be more environmental friendly as they are biodegradable, renewable, and readily available in natural form and possess adequate strength. They offer more economical and environmental advantages and start to become emerging materials in engineering field (Lau *et al.*, 2018).

A study by Mohamed and Appanah (1998) showed that only 0.6 million tons of bamboo stocks in Malaysia that are being used commercially instead of the total amount of 7.0 million tons. Based on the statistic, this quantity has reached an estimated value of RM 3 million. Due to the rapid growth rate of bamboo and its great productivity, bamboos production has reached a huge amount of 30,000,000 tons (Faruk *et al.*, 2012). Bamboos are the largest green grass family *Poaceae* in the subfamily *Bambusoideae*. There are more than thousand species of bamboo found in diverse climate (Eichhorn *et al.*, 2001). Out of these, 18 bamboo species have been used as fiber for composites. Therefore, suitable and convenient methods should be implemented to fabricate bamboo composites and optimize its benefit as natural resources (Okubo, Fujii and Yamamoto, 2004).

Bamboo fibers are also called `natural glass fiber` due to its longitudinal alignment of fibers which produces high strength with respect to its weight. High performance composite parts are produced from these fiber configurations at low implementation cost with the help of advance technology (Perremans *et al.*, 2018). Compare to other natural fibers, bamboo fiber also has lower cellulose content and a smaller microfibrillar angle which contribute to both volume resistivity and mechanical strength. Those cellulose fibers inside the bamboo composite material are embedded in lignin matrix, aligned along the length of the bamboo which then produces maximum flexural strength, rigidity and tensile (Ray, Das and Mondal, 2004). Due to the superior tensile strength and modulus of elasticity, bamboo fibers become common materials used in polymeric composites (Deshpande et al. 2000). Another research showed that the tensile strength of bamboo fiber reached a high value about 330 MPa which is higher than other natural fiber reinforced green composites (Cao, Shibata and Fukumoto, 2006).

Bio-composites made of bamboo fibers are considered as green and environmentally responsible eco-products. Epoxy resins are used as the matrix in the fabrication of composite plates. With the combination of two materials, it can enhance the stiffness, flexural, tensile strength, and resistance to corrosion of the composites plate. They are preferable to be installed externally as structural material to strengthen the reinforced structures due to its light weight, ease in installation, high strength and abundant resources (Chin *et al.*, 2012). Therefore, it is possible to increase the number of application for bamboo fiber reinforced composite plate to replace the costly and non-biodegradable synthetic fibers. In the latest development, the interest of utilizing natural fiber was shifted to the aerospace industry (interior), automotive, marine and even civil construction materials (Bansal, Ramachandran and Raichurkar, 2017).

The strengthening of existing civil structures must be considered when environment factors such as moisture and weathering affect the lifespan of the whole buildings (Alam and Al Riyami, 2018). To extend the design life of the structure, several strengthening methods like applying the bolts, widening the span and externally bonded fiber reinforced plates on RC structures have been implemented (Jumaat and Alam, 2008). These applications tend to repair and upgrade the existing structures in term of design life time and load bearing capacity.

## **1.2 Problem Statement**

The fabrication of composite plate is commenced by using synthetic fibers due to their high strength, stiffness and longer life span. Moreover, synthetic fiber composite plates (SFCPs) tend to be more resistant to corrosion, water, adverse environment and thermal stability (Begum K and Islam MA, 2013). These unique characteristics enable them to be adapted and equipped easily on most structures. Despite these advantages, SFCPs have plenty of drawbacks and the biggest restriction is the high production cost. They are also non-biodegradable as this would lead to environment hazards as the fabrication process produces a significant amount of carbon dioxide gaseous (CO<sub>2</sub>). Based on these reasonable analyses, renewable natural plant fibers composites are increasingly gaining attention as viable alternative to SFCPs over years.

Although natural plant fibers especially bamboo fibers are taking advantage of strong material properties and environmental friendly, it has a low comprehensive utilization rate and automation. The problem is that the bamboo industry produces no high value products and it fails to maximize the ecological and economic strengths (Wang et al., 2013). Although a great work has been made on potential of natural fiber composite materials as alternative solution in construction industries, research on the suitability of bamboo fiber composite plates (BFCP) for externally strengthening the reinforced concrete structures is rare.

All these issues have led to explore of possible BFCP to replace some of the traditional engineering materials that are not environmentally friendly which used and resolve these issues. Natural plant fibers have unequivocally contributed economic prosperity and sustainability in our daily lives. To this end, in the present research work, an attempt has been made to reveal the physical and mechanical properties of bamboo fiber as well as the potential of BFCP to be used as external strengthening materials on RC structures.

## **1.3 Research Objectives**

The aims of this research are to study the mechanical properties of bamboo specimens (Betung species) as well as the fabricated bamboo fiber composite plate (BFCP) followed by the applicability of its composite plates for external strengthening on RC beams. The objectives of the research work are specified as follow:

## REFERENCES

- Abdul Khalil, H. P. S. *et al.* (2012) 'Bamboo fibre reinforced biocomposites: A review', *Materials and Design*. Elsevier Ltd, 42, pp. 353–368. doi: 10.1016/j.matdes.2012.06.015.
- Al-bahadly, E. A. O. (2013) 'The Mechanical Properties of Natural Fiber Composites', 2013, pp. 1–228.
- Alam, M. A., Hassan, A. and Muda, Z. C. (2016) 'Development of kenaf fibre reinforced polymer laminate for shear strengthening of reinforced concrete beam', *Materials and Structures*. Springer Netherlands, 49(3), pp. 795–811. doi: 10.1617/s11527-015-0539-0.
- Alam, M. A. and Al Riyami, K. (2018) 'Shear strengthening of reinforced concrete beam using natural fibre reinforced polymer laminates', *Construction and Building Materials*. Elsevier Ltd, 162, pp. 683–696. doi: 10.1016/j.conbuildmat.2017.12.011.
- Amada, S. *et al.* (1997) 'Fiber texture and mechanical graded structure of bamboo', *Composites Part B: Engineering*, 28(1–2), pp. 13–20. doi: 10.1016/S1359-8368(96)00020-0.
- Ashimori, M. *et al.* (2004) 'Study on Splitting of Bamboo Fibers Due to Freezing and Tensile Strength of FRTP Using Bamboo Fibers', *JSME International Journal Series A*, 47(4), pp. 566–569. doi: 10.1299/jsmea.47.566.
- Avila, A. F. and Morais, D. T. S. (2005) 'A multiscale investigation based on variance analysis for hand lay-up composite manufacturing', *Composites Science and Technology*, 65(6), pp. 827–838. doi: 10.1016/j.compscitech.2004.05.021.
- Aziz, S. H. *et al.* (2005) 'Modified polyester resins for natural fibre composites', *Composites Science and Technology*, 65(3–4), pp. 525–535. doi: 10.1016/j.compscitech.2004.08.005.
- Bansal, S., Ramachandran, M. and Raichurkar, P. (2017) 'Comparative Analysis of Bamboo using Jute and Coir Fiber Reinforced Polymeric Composites', *Materials Today: Proceedings*. Elsevier Ltd, 4(2), pp. 3182–3187. doi: 10.1016/j.matpr.2017.02.203.
- Begum K and Islam MA (2013) 'Natural Fiber as a substitute to Synthetic Fiber in Polymer Composites: A Review', *Research Journal of Engineering Sciences ISSN Res. J. Engineering Sci*, 2(3), pp. 2278–9472. doi: 10.13140/RG.2.1.2685.6163.
- Belgacem, M. and Gandini, A. (2008) *Monomers, Polymers and Composites from Renewable Resources*, *Monomers, Polymers and Composites from Renewable Resources*. doi: 10.1016/B978-0-08-045316-3.00013-2.

- Biswas, S. *et al.* (2015) 'Physical, mechanical and thermal properties of jute and bamboo fiber reinforced unidirectional epoxy composites', *Procedia Engineering*. Elsevier B.V., 105(Icte 2014), pp. 933–939. doi: 10.1016/j.proeng.2015.05.118.
- Buckingham, K. *et al.* (2011) 'The potential of bamboo is constrained by outmoded policy frames', *Ambio*, 40(5), pp. 544–548. doi: 10.1007/s13280-011-0138-4.
- Buckingham, K. C., Wu, L. and Lou, Y. (2014) 'Can't See the (Bamboo) Forest for the Trees: Examining Bamboo's Fit Within International Forestry Institutions', *Ambio*, 43(6), pp. 770–778. doi: 10.1007/s13280-013-0466-7.
- Budi, A. S. and Rahmadi, A. P. (2017) 'Performance of wulung bamboo reinforced concrete beams', *AIP Conference Proceedings*, 1903. doi: 10.1063/1.5011490.
- Cao, Y., Shibata, S. and Fukumoto, I. (2006) 'Evaluation of statistical strength of bamboo fiber and mechanical properties of fiber reinforced green composites', *Composites: Part A* 37 (2006) 423–429, pp. 423–429. doi: 10.1007/s11771.
- Chaowana, P. and Barbu, M. C. (2017) *Bamboo, Lignocellulosic Fibre and Biomass-Based Composite Materials*. Elsevier Ltd. doi: 10.1016/B978-0-08-100959-8.00013-5.
- Chin, S. C. *et al.* (2012) 'Strengthening of RC beams with large openings in shear by CFRP laminates', *International Science Index*, (March), pp. 1–6.
- Costa, M. M. E. *et al.* (2017) 'Influence of physical and chemical treatments on the mechanical properties of bamboo fibers', *Procedia Engineering*. Elsevier B.V., 200, pp. 457–464. doi: <https://doi.org/10.1016/j.proeng.2017.07.064>.
- Deshpande, A. P., Bhaskar Rao, M. and Lakshmana Rao, C. (2000) 'Extraction of bamboo fibers and their use as reinforcement in polymeric composites', *Journal of Applied Polymer Science*, 76(1), pp. 83–92. doi: 10.1002/(SICI)1097-4628(20000404)76:1<83::AID-APP11>3.0.CO;2-L.
- Eichhorn, S. J. *et al.* (2001) 'Current international research into cellulosic fibres and composites', *Journal of Materials Science*, 36(9), pp. 2107–2131. doi: 10.1023/A:1017512029696.
- Faruk, O. *et al.* (2012) 'Biocomposites reinforced with natural fibers: 2000-2010', *Progress in Polymer Science*. Elsevier Ltd, 37(11), pp. 1552–1596. doi: 10.1016/j.progpolymsci.2012.04.003.
- Ghavami, K. (1995) 'Ultimate load behaviour of bamboo-reinforced lightweight concrete beams', *Cement and Concrete Composites*, 17(4), pp. 281–288. doi: 10.1016/0958-9465(95)00018-8.

- Gojny, F. H. *et al.* (2005) 'Influence of different carbon nanotubes on the mechanical properties of epoxy matrix composites - A comparative study', *Composites Science and Technology*, 65(15–16 SPEC. ISS.), pp. 2300–2313. doi: 10.1016/j.compscitech.2005.04.021.
- Gratani, L. *et al.* (2008) 'Growth pattern and photosynthetic activity of different bamboo species growing in the Botanical Garden of Rome', *Flora: Morphology, Distribution, Functional Ecology of Plants*, 203(1), pp. 77–84. doi: 10.1016/j.flora.2007.11.002.
- Gupta, A. K., Ganguly, R. and Mehra, A. S. (2015) 'Bamboo as green alternative to steel for reinforced concrete elements of a low cost residential building', *Electronic Journal of Geotechnical Engineering*, 20(6), pp. 1523–1545.
- Haghighatnia, T., Abbasian, A. and Morshedian, J. (2017) 'Hemp fiber reinforced thermoplastic polyurethane composite: An investigation in mechanical properties', *Industrial Crops and Products*. Elsevier, 108(December 2016), pp. 853–863. doi: 10.1016/j.indcrop.2017.07.020.
- Ho, M. *et al.* (2012) 'Critical factors on manufacturing processes of natural fibre composites', *Composites Part B: Engineering*. Elsevier Ltd, 43(8), pp. 3549–3562. doi: 10.1016/j.compositesb.2011.10.001.
- Indra Reddy, M. *et al.* (2018) 'Comparative Evaluation on Mechanical Properties of Jute, Pineapple leaf fiber and Glass fiber Reinforced Composites with Polyester and Epoxy Resin Matrices', *Materials Today: Proceedings*. Elsevier Ltd, 5(2), pp. 5649–5654. doi: 10.1016/j.matpr.2017.12.158.
- Jawaaid, M. and Abdul Khalil, H. P. S. (2011) 'Cellulosic/synthetic fibre reinforced polymer hybrid composites: A review', *Carbohydrate Polymers*. Elsevier Ltd., 86(1), pp. 1–18. doi: 10.1016/j.carbpol.2011.04.043.
- Joshi, S. V. *et al.* (2004) 'Are natural fiber composites environmentally superior to glass fiber reinforced composites?', *Composites Part A: Applied Science and Manufacturing*, 35(3), pp. 371–376. doi: 10.1016/j.compositesa.2003.09.016.
- Jumaat, M. Z. and Alam, M. A. (2008) 'Behaviour of U and L shaped end anchored steel plate strengthened reinforced concrete beams', *European Journal of Scientific Research*, 22(2), pp. 184–196. Available at: <http://www.scopus.com/inward/record.url?eid=2-s2.0-55249120258&partnerID=40&md5=d921a7d0304b636e5dd197eda2fba0a1>.
- Kaur, V., Chattopadhyay, D. P. and Kaur, S. (2013) 'Study on Extraction of Bamboo Fibres from Raw Bamboo Fibres Bundles Using Different Retting Techniques', *Textiles and Industrial Science and Technology (TLIST)*, 2(4), pp. 174–179. Available at: <http://www.seipub.org/tlist/paperInfo.aspx?ID=5427>.

- Keck, S. and Fulland, M. (2016) 'Effect of fibre volume fraction and fibre direction on crack paths in flax fibre-reinforced composites', *Engineering Fracture Mechanics*. Elsevier Ltd, 167, pp. 201–209. doi: 10.1016/j.engfracmech.2016.03.037.
- Krishna Adhikari, R. and Keerthi Gowda, B. S. (2017) 'Exploration of mechanical properties of banana/jute hybrid polyester composite', *Materials Today: Proceedings*. Elsevier Ltd, 4(8), pp. 7171–7176. doi: 10.1016/j.matpr.2017.07.043.
- Kushwaha, P. K. and Kumar, R. (2010) 'Studies on Performance of Acrylonitrile-Pretreated Bamboo-Reinforced Thermosetting Resin Composites', *Journal of Reinforced Plastics and Composites*, 29(9), pp. 1347–1352. doi: 10.1177/0731684409103701.
- Lau, K. tak *et al.* (2018) 'Properties of natural fibre composites for structural engineering applications', *Composites Part B: Engineering*. Elsevier, 136(October 2017), pp. 222–233. doi: 10.1016/j.compositesb.2017.10.038.
- Lim, S. P. (2017) *External Strengthening of Reinforced Concrete Beams With Bamboo Fiber-Vinyl Ester Composite Plate*.
- Liu, D. *et al.* (2012) 'Bamboo fiber and its reinforced composites: Structure and properties', *Cellulose*, 19(5), pp. 1449–1480. doi: 10.1007/s10570-012-9741-1.
- Lo, T. Y., Cui, H. Z. and Leung, H. C. (2004) 'The effect of fiber density on strength capacity of bamboo', *Materials Letters*, 58(21), pp. 2595–2598. doi: 10.1016/j.matlet.2004.03.029.
- Manalo, A. C. *et al.* (2015) 'Effects of alkali treatment and elevated temperature on the mechanical properties of bamboo fibre-polyester composites', *Composites Part B: Engineering*. Elsevier Ltd, 80, pp. 73–83. doi: 10.1016/j.compositesb.2015.05.033.
- Mandal, S. *et al.* (2010) 'Studies on Bamboo/Glass Fiber Reinforced USP and VE Resin', *Journal of Reinforced Plastics and Composites*, 29(1), pp. 43–51. doi: 10.1177/0731684408095048.
- Marsh, J. and Smith, N. (2007) 'New bamboo industries and pro-poor impacts: lessons from China and potential for Mekong Countries', *International Conference on managing forests for poverty reduction: capturing opportunities in forest harvesting and wood processing for the benefit of the poor*, pp. 1–21.
- Mohamed, A. H. J. *et al.* (2007) 'Quality management of the bamboo resource and its contribution to environmental conservation in Malaysia', *Management of Environmental Quality: An International Journal*, 18(6), pp. 643–656. doi: 10.1108/14777830710826685.
- Mohanty, S. and Nayak, S. K. (2010) 'Short Bamboo Fiber-reinforced HDPE Composites: Influence of Fiber Content and Modification on Strength of the Composite', *Journal of Reinforced Plastics and Composites*, 29(14), pp. 2199–2210.

- Monteiro, S. N. *et al.* (2011) 'Natural lignocellulosic fibers as engineering materials-An overview', *Metallurgical and Materials Transactions A: Physical Metallurgy and Materials Science*, 42(10), pp. 2963–2974. doi: 10.1007/s11661-011-0789-6.
- O'Donnell, A., Dweib, M. A. and Wool, R. P. (2004) 'Natural fiber composites with plant oil-based resin', *Composites Science and Technology*, 64(9), pp. 1135–1145. doi: 10.1016/j.compscitech.2003.09.024.
- Okubo, K., Fujii, T. and Yamamoto, Y. (2004) 'Development of bamboo-based polymer composites and their mechanical properties', *Composites Part A: Applied Science and Manufacturing*, 35(3), pp. 377–383. doi: 10.1016/j.compositesa.2003.09.017.
- Osorio, L. *et al.* (2011) 'Morphological aspects and mechanical properties of single bamboo fibers and flexural characterization of bamboo/ epoxy composites', *Journal of Reinforced Plastics and Composites*, 30(5), pp. 396–408. doi: 10.1177/0731684410397683.
- Padmaraj, N. H. *et al.* (2018) 'Mechanical Characterization of Areca husk-Coir fiber reinforced hybrid Composites', *Materials Today: Proceedings*. Elsevier Ltd, 5(1), pp. 1292–1297. doi: 10.1016/j.matpr.2017.11.214.
- Perremans, D. *et al.* (2018) 'Effect of discontinuities in bamboo fibre reinforced epoxy composites', *Composites Science and Technology*. Elsevier Ltd, 155, pp. 50–57. doi: 10.1016/j.compscitech.2017.11.033.
- Phong, N. T. *et al.* (2011) 'Study on How to Effectively Extract Bamboo Fibers from Raw Bamboo and Wastewater Treatment', *Journal of Materials Science Research*, 1(1), pp. 144–155. doi: 10.5539/jmsr.v1n1p144.
- Ramana, M. V. and Ramprasad, S. (2017) 'Experimental Investigation on Jute/Carbon Fibre reinforced Epoxy based Hybrid Composites', *Materials Today: Proceedings*, 4(8), pp. 8654–8664. doi: 10.1016/j.matpr.2017.07.214.
- Ramesh, M., Palanikumar, K. and Reddy, K. H. (2017) 'Plant fibre based bio-composites: Sustainable and renewable green materials', *Renewable and Sustainable Energy Reviews*. Elsevier Ltd, 79(February), pp. 558–584. doi: 10.1016/j.rser.2017.05.094.
- Ratna Prasad, A. V. and Mohana Rao, K. (2011) 'Mechanical properties of natural fibre reinforced polyester composites: Jowar, sisal and bamboo', *Materials and Design*. Elsevier Ltd, 32(8–9), pp. 4658–4663. doi: 10.1016/j.matdes.2011.03.015.
- Ray, A. K., Das, S. K. and Mondal, S. (2004) 'Microstructural characterization of bamboo', 9, pp. 1055–1060.



- Satyanarayana, K. G., Guimarães, J. L. and Wypych, F. (2007) 'Studies on lignocellulosic fibers of Brazil. Part I: Source, production, morphology, properties and applications', *Composites Part A: Applied Science and Manufacturing*, 38(7), pp. 1694–1709. doi: 10.1016/j.compositesa.2007.02.006.
- Scarponi, C. *et al.* (2016) 'Low-velocity impact behaviour of hemp fibre reinforced bio-based epoxy laminates', *Composites Part B: Engineering*, 91(2016), pp. 162–168. doi: 10.1016/j.compositesb.2016.01.048.
- Sen, T. and Reddy, H. N. J. (2014) 'Flexural strengthening of RC beams using natural sisal and artificial carbon and glass fabric reinforced composite system', *Sustainable Cities and Society*. Elsevier B.V., 10, pp. 195–206. doi: 10.1016/j.scs.2013.09.003.
- Senthil Kumar, K. *et al.* (2014) 'Synergy of fiber length and content on free vibration and damping behavior of natural fiber reinforced polyester composite beams', *Materials & Design (1980-2015)*. Elsevier Ltd, 56, pp. 379–386. doi: 10.1016/j.matdes.2013.11.039.
- Shi, Q. F. *et al.* (2012) 'Influence of Heat Treatment on the Heat Distortion Temperature of Poly(lactic acid)/Bamboo Fiber/Talc Hybrid Biocomposites', *Polymers and Polymer Composites*. doi: 10.1002/app.
- Soykeabkaew, N., Supaphol, P. and Rujiravanit, R. (2004) 'Preparation and characterization of jute-and flax-reinforced starch-based composite foams', *Carbohydrate Polymers*, 58(1), pp. 53–63. doi: 10.1016/j.carbpol.2004.06.037.
- Swapnil, A. S. *et al.* (2017) 'Experimental Investigation of Mechanical Properties of Glass Fibre/Epoxy Composites with variable volume fraction', *Materials Today: Proceedings*, 4(9), pp. 9487–9490. doi: 10.1016/j.matpr.2017.06.209.
- Taj, S. (2014) 'Natural fiber-reinforced polymer composites', (October).
- Takagi, H. and Ichihara, Y. (2004) 'Effect of Fiber Length on Mechanical Properties of "Green" Composites Using a Starch-Based Resin and Short Bamboo Fibers', *JSME International Journal Series A*, 47(4), pp. 551–555. doi: 10.1299/jsmea.47.551.
- Tong, F. S. (2017) 'Strengthening of Rc Beams With Openings Using Bamboo Fiber Reinforced Composite ( Bfrc ) Plates'.
- Trujillo, E. *et al.* (2013) 'Assessment of the Properties of Bamboo Fibre and Bamboo Fibre Composites', *Composites Week @ Leuven and Texcomp-11 Conference*, pp. 16–20.
- Verma, C. S. *et al.* (2017) 'Mechanical Properties of Bamboo Laminates with other composites', *Materials Today: Proceedings*. Elsevier Ltd, 4(2), pp. 3380–3386. doi: 10.1016/j.matpr.2017.02.226.

- Wai, N. N., Nanko, H. and Murakami, K. (1985) 'A morphological study on the behavior of bamboo pulp fibers in the beating process', *Wood Science and Technology*, 19(3), pp. 211–222. doi: 10.1007/BF00392050.
- Wang, X. *et al.* (2012) 'Cell wall structure and formation of maturing fibres of moso bamboo (*Phyllostachys pubescens*) increase buckling resistance', *Journal of The Royal Society Interface*, 9(70), pp. 988–996. doi: 10.1098/rsif.2011.0462.
- Yao, W. and Zhang, W. (2011) 'Research on manufacturing technology and application of natural bamboo fibre', *Proceedings - 4th International Conference on Intelligent Computation Technology and Automation, ICICTA 2011*, 2, pp. 143–148. doi: 10.1109/ICICTA.2011.327.
- Zakikhani, P. *et al.* (2014) 'Extraction and preparation of bamboo fibre-reinforced composites', *Materials and Design*. Elsevier Ltd, 63, pp. 820–828. doi: 10.1016/j.matdes.2014.06.058.
- Zhang, Y. *et al.* (2014) 'Thermoset-thermoplastic hybrid nanoparticles and composite coatings', *Polymer (United Kingdom)*. Elsevier Ltd, 55(10), pp. 2305–2315. doi: 10.1016/j.polymer.2014.02.052.
- ZhaoHua, L. and Kobayashi, M. (2004) 'Plantation future of bamboo in China.', *Journal of Forestry Research*, 15(3), pp. 233–242. doi: 10.1007/BF02911032.
- Zhou, B.-Z. *et al.* (2005) 'Ecological functions of bamboo forest: Research and Application', *Journal of Forestry Research*, 16(2), pp. 143–147. doi: 10.1007/BF02857909.